



ABSTRACT

Liquid thermosetting ink for ink-jet applications includes at least a resin, at least one solid latent curing agent having a maximal particle size of less than 2 microns and an inert filler having fine particles. The single-pack or two-pack ink has a viscosity lower than 50 Cp at the application temperature, a surface tension lower than 80 dyn/cm at the application temperature, and a glass transition temperature of cured ink of greater than 120°C.